



Robertson Microlit Laboratories

1705 U.S. Highway 46 / Suite 1D / Ledgewood, NJ 07852 / (973) 966-6668 / Fax: (973) 966-0136
www.robertson-microlit.com results@robertson-microlit.com

Naresh Patel
ITW Pro Brands

Date: 5/8/17

Results of Analysis
Sample Number:
High Purity Black F.T. Q404 Test #761

Analysis	Results (ppm)	Requirements (ppm)
<i>Total Halogens</i>	250 maximum
Bromine	<2ppm	100 maximum
Chlorine	27ppm	100 maximum
Fluorine	<1ppm	100 maximum
Iodine	<9ppm	100 maximum
Lead	<1ppm	25 maximum
Sulfur	20ppm	250 maximum
<i>Low Melting Point Elements</i>	300 maximum
Antimony	<1ppm	100 maximum
Bismuth	<1ppm	100 maximum
Boron	1ppm	100 maximum
Cadmium	<1ppm	100 maximum
Copper	1ppm	100 maximum
Mercury	<1ppm	100 maximum
Phosphorus	<1ppm	100 maximum
Selenium	<1ppm	100 maximum
Silver	<1ppm	100 maximum
Sodium	6ppm	100 maximum
Tellurium	<1ppm	100 maximum
Thallium	<1ppm	100 maximum
Tin	<1ppm	100 maximum
Zinc	3ppm	100 maximum

Meets GE Specifications #D50TF8

QA:


Dr. Robert Di Vincenzo